

MIL-HDBK-1002/5
30 MARCH 1987

SUPERSEDING
NAVFAC DM-2.5
MAY 1980

MILITARY HANDBOOK

TIMBER STRUCTURES



NO DELIVERABLE DATA REQUIRED BY THIS DOCUMENT

DISTRIBUTION STATEMENT A. APPROVED FOR PUBLIC RELEASE: DISTRIBUTION IS UNLIMITED

AREA FACR

MIL-HDBK-1002/5

THIS PAGE IS INTENTIONALLY BLANK

MIL-HDBK-1002/5

ABSTRACT

Basic criteria for the design of timber structural elements and timber structural systems are presented for use by experienced engineers. The contents cover general topics concerning design standards for bridge and building structures and details of design. A section on selection of species and grade of timber is included. Special considerations in the design of plywood elements and of built-up members, problems of wood preservation and termite control, fire retardant treatment, and climatic influences are discussed.

MIL-HDBK-1002/5

THIS PAGE IS INTENTIONALLY BLANK

MIL-HDBK-1002/5

FOREWORD

This military handbook is one of a series of criteria manuals developed from an evaluation of facilities in the shore establishment, from surveys of the availability of new materials and construction methods, and from selection of the best design practices of the Naval Facilities Engineering Command, other Government agencies, and the private sector. It uses to the maximum extent feasible, national professional society, association, and institute standards.

Design cannot remain static any more than can the functions it serves or the technologies it uses. Accordingly,, recommendations for improvement are encouraged and should be furnished to Naval Facilities Engineering Command, Northern Division, Code 04AB, Philadelphia, PA 19112-5094; telephone (215) 897-6153.

This handbook shall not be used as a reference document for procurement. Do not reference it in Military or Federal specifications or other procurement documents.

MIL-HDBK-1002/5

THIS PAGE IS INTENTIONALLY BLANK

MIL-HDBK-1002/5

TIMBER STRUCTURES

CONTENTS

	<u>Page</u>
Section 1	SCOPE AND RELATED CRITERIA. 1
1.1	Scope 1
1.2	Cancellation. 1
1.3	Related Criteria. 1
1.4	Standard Specifications 1
Section 2	DESIGN STANDARDS. 3
2.1	Class A Structures. 3
2.1.1	Highway Bridges 3
2.1.2	Railway Bridges 3
2.1.3	Other 3
2.1.4	Plywood Members 3
2.2	Class B and Class C Structures. 3
2.2.1	Lumber and Timber, Including Glue-Laminated Members 3
2.2.1.1	Sealers 3
2.2.1.2	Connections 3
2.2.1.3	Hardware. 3
2.3	Plywood 3
2.4	Light Wood Trusses. 3
2.4.1	Light Metal Plate Connected to Wood Trusses 3
2.4.2	Glued-Nailed Trussed Rafters. 4
Section 3	DETAILS OF DESIGN 5
3.1	Selection of Species and Grade. 5
3.1.1	General 5
3.1.1.1	Stress Grade Lumber 5
3.1.1.2	Nonstress Grade Lumber. 5
3.1.1.3	Plywood 5
3.1.1.4	Durability. 5
3.1.2	Nondomestic Species of Timber 5
3.1.2.1	Properties. 5
3.1.1.2	Allowable Stresses. 5
3.2	Special Considerations. 5
3.2.1	Mechanically Laminated Members. 8
3.2.2	Plywood Members 8
3.2.2.1	Built-up Plywood Girders. 8
3.2.2.2	Stress-Skin Panels. 8
3.2.2.3	Exposure. 8
3.2.3	Glued, Built-up (Including Laminated) Members 8
3.2.3.1	Transverse Joints 8
3.2.3.2	Mechanical Fasteners. 8
3.2.3.3	Exposure. 9
3.2.4	Wood Preservation 9
3.2.4.1	Preservative Treatment. 9
3.2.4.2	Structural Framing. 9
3.2.4.3	Frame Before Treatment. 9

MIL-HDBK-1002/5

	<u>Page</u>
3.2.4.4 Site Requirements	9
3.2.5 Fire Retardant Treatment.	10
3.2.6 Climatic Influences	10
3.2.6.1 Cold Region Conditions.	10
3.2.6.2 Tropical Conditions	10
3.2.7 Limited Life Structures	10
3.2.8 Termite Control	10

FIGURES

1 Properties of Nondomestic Species of Timber.	6
REFERENCES	11

MIL-HDBK-1002/5

Section 1: SCOPE AND RELATED CRITERIA

1.1 Scope. This handbook prescribes criteria for the design of structures, including temporary structures, which are fabricated of timber and related materials.

This handbook shall not be used as a reference document for procurement purposes. Do not reference it in Military or Federal specifications or other procurement documents.

1.2 Cancellation. This handbook, MIL-HDBK-1002/5, Timber Structures, cancels and supersedes NAVFAC DM-2.5, Timber Structures of May 1980.

1.3 Related Criteria. Certain criteria related to the design of timber structures appear in other design guidance, as follows:

<u>Subject</u>	<u>Source</u>
Service Classification and Other General Requirements	NAVFAC DM-2.01, General Requirements
Foundations	NAVFAC DM-7.02, Foundations and Earth Structures
Fire Protection	MIL-HDBK-1008, Fire Protection for Facilities Engineering, Design, and Construction
Bridges	AASHTO Standard Specification for Highway Bridges
	AREA Manual for Railway Engineering
Timber	NFPA National Design Specifica- tion for Wood Construction
	AITC Timber Construction Manual
	APA Plywood Design Specification
	TPI Design Specification for Light Metal Plate Connected Wood Trusses

1.4 Standard Specifications. Throughout this handbook, where design criteria are obtained from cited sources, those citations are termed "standard specifications."

MIL-HDBK-1002/5

THIS PAGE IS INTENTIONALLY BLANK

MIL-HDBK-1002/5

Section 2: DESIGN STANDARDS

2.1 Class A Structures.

2.1.1 Highway Bridges. American Association of State Highway and Transportation Officials (AASHTO) Standard, Standard Specifications for Highway Bridges, applies.

2.1.2 Railway Bridges. American Railway Engineering Association (AREA) Standard, Manual for Railway Engineering, applies.

2.1.3 Other. Unless special considerations exist, the AASHTO Standard, Standard Specifications for Highway Bridges, applies. Specifically, the AASHTO Standard may be followed in the design of structures supporting equipment moving on tracks (except where classified Class B in DM-2.01) if the provisions for distribution of concentrated loads are modified to reflect the effects of the tracks.

2.1.4 Plywood Members. Allowable stresses shall be 90 percent of the values for Class B and Class C structures.

2.2 Class B and Class C Structures.

2.2.1 Lumber and Timber, Including Glue-Laminated Members. National Fire Protection Association (NFPA) Standard, National Design Specification for Wood Construction, applies. Additional criteria and design applications are contained in American Institute of Timber Construction (AITC) Timber Construction Manual.

2.2.1.1 Sealers. Where feasible, minimize seasoning checks in the ends of timber pieces installed in an unseasoned condition by the use of end coating or sealers.

2.2.1.2 Connections. Detail connections to permit periodic tightening.

2.2.1.3 Hardware. Bore bolt holds for drift bolts with a bit having a diameter of 1/8 inch (3 mm) less than the bolt diameter.

2.3 Plywood. American Plywood Association (APA) Standard, Plywood Design Specification, including the supplements listed in the appendix, and American Plywood Association (APA) publications Plywood Folded Plates and Plywood Diaphragm Construction, apply. For plywood treated with fire-retardant salts, reduce physical properties in APA standards by:

Modulus of elasticity (E) - 10 percent

Modulus of Rupture (G) - 20 percent

2.4 Light Wood Trusses.

2.4.1 Light Metal Plate Connected to Wood Trusses. Design in conformance with Sections 200 and 300 of Truss Plate Institute (TPI) Design Specifications for Light Metal Plate Connected Wood Trusses.

MIL-HDBK-1002/5

2.4.2 Glued-Nailed Trussed Rafters. Design in accordance with the method and data described in the Purdue University Agricultural Experiment Station Research Bulletins No. 714, Determination of Member Stresses in Wood Trusses with Right Joints, and No. 727, The Design of Glued Joints for Wood Trusses and Frames.

MIL-HDBK-1002/5

Section 3: DETAILS OF DESIGN

3.1 Selection of Species and Grade.3.1.1 General

3.1.1.1 Stress Grade Lumber. Design values shall be in accordance with the species and grade selected from the NFPA Standard. Where preservative treatment is required, selection of species should consider ease and efficacy of treatment.

3.1.1.2 Nonstress Grade Lumber. Nonstress grade lumber may be used for miscellaneous framing such as nailers, caps, bucks, grounds, sleepers, blocking, bridging, plates, and furrings. Such members shall be "Standard" grade or better.

3.1.1.3 Plywood. Plywood shall be of species groups 1, 2, or 3, as classified in the APA Standard.

3.1.1.4 Durability. See data in U.S. Department of Agriculture (USDA) Wood Handbook.

3.1.2 Nondomestic Species of Timber.

3.1.2.1 Properties. Many nondomestic species of timber are suitable for construction work. Some have very high strength and are more durable than softwoods. Resistance to attack by marine borers is claimed for some species, but performance data suggest that such resistance is not reliable. A partial listing of nondomestic timbers and their properties is contained in Table 1, Properties of Nondomestic Species of Timber. Items of particular interest are:

a) Pressure preservative treated Apitong (*Dipterocarpus grandiflorus* blanco) is highly suitable for wood piling and utility poles.

b) The tropical woods Ipil (*Intsia bijuga*), Daog or Palomara (*Calophyllum inophyllum*), Ahgao (*Premna obtusifolia*), Fago (*Ocrosia oppositifolia*), Yacal (*Hopea*, *Sborea*, and *Isoptera* species), Molave (*Vitex parviflora* Juss), and Chopag (*Ocrocarpus odoratus*) are satisfactory for most structural uses. Use Redwood structurally only in cooling towers.

c) Use the following tropical woods on Guam only when construction is to be of a temporary nature: Coconut (*Cocos nucifera*), Dugdug (*Artocarpus* sp.), Nunu (*Ficus prolixa*), Yoga (*Elacocarpus joga*), and Faya (*Tristiropsis obtusangula*).

3.1.1.2 Allowable Stresses. Obtain strength properties of individual species from the potential supplier. Allowable stresses should be one-fourth to one-third of the ultimate strengths. Regard characteristics as published by the supplier with caution and insist on tests of random specimens to verify assumed strength characteristics.

3.2 Special Considerations.

Region	Name	Bending Strength	Hardness	Shock Resistance	Specific Gravity	Durability	Marine Borer Resistance	Availability
British Guiana	Greenheart	Very Strong	Very Hard	Good	0.93	Good	Fair	Abundant
French Guiana	Angelique	Strong	Strong	Hard	0.72	Good	Fair	Fair
Brazil	Piquia	Strong	Hard	Good	0.88	Good	Fair	*
British Guiana	Maristribaili	Very Strong	Very Hard	Good	1.09	Excellent	Excellent	*
South America	Acapu	Strong	Hard	Good	0.95	Good	Good	Fair
British Guiana	Black Kakeralli	Strong	Very Hard	Good	1.00	Excellent	Excellent	*
Western Pacific Region	Aroeng	Strong	Hard	Good	0.83	Good	Good	Fair
Western Pacific Region	Ipil	Very Strong	Very Hard	Good	0.78	Good	Good	Limited
Western Pacific Region	Kasi-Kasi	Fair	Hard	Good	0.61	Good	Very Good	Fair
Western Pacific Region	Dungon-late	Strong	Hard	Good	1.01	Good	Very Good	Fair
Western Pacific Region	Pagatpat	Strong	Hard	Good	1.03	Good	Good	Fair
Western Pacific Region	Bogoia	Strong	Hard	Good	1.14	Good	Very Good	Plentiful
Philippine Islands	Anubing	Fair	Moderate	Good	0.75	Good	Very Good	Fair
Philippine Islands	Alupag	Strong	Hard	Fair	0.97	Very Good	Good	Limited
Philippine Islands	Apitong	Strong	Hard	Good	0.80	Creosoting Recommended	Good	Plentiful
Philippine Islands	Bensalagin	Strong	Very Hard	Good	1.06	Good	Fair	Fair
Philippine Islands	Kalamansanasi	Strong	Very Hard	Good	0.93	Fair	Fair	Fair
Philippine Islands and New Guinea	Narig	Very Strong	Very Hard	Good	0.97	Good	Very Good	Fair
New Britain and New Guinea	Komo Kamarere	Strong	Hard	Good	0.83	Good	Fair	Fair
New Britain and Bismarck	Malasa	Strong	Hard	Good	0.97	Good	Good	Fair
New Britain and Moluccas	Zizanu	Good	Hard	Good	0.75	Good	Good	Plentiful
South Papua	Paper-bark	Strong	Very Hard	Fair	**	Good	Good	Abundant

* Obtain availability from local sources

** Obtain data from local sources

Figure 1
Properties of Nondomestic Species of Timber

Region	Name	Bending Strength	Hardness	Shock Resistance	Specific Gravity	Durability	Marine Borer Resistance	Availability
South China Sea Region	Kiet-mouk	Strong	Hard	Good	0.97	Good	Fair	Fair
South China Sea Region	Doengon	Strong	Hard	Good	1.01	Good	Fair	Fair
South China Sea Region	Sehg Kang Wang	Strong	Very Hard	Good	1.04	Very Durable	Good	Fair
South China Sea Region	Bakau-belakup	Strong	Hard	Good	0.99	Durable	Good	Plentiful
South China Sea Region	Baratlauk	Very Strong	Hard	Good	1.11	Very Durable	Good	Fair
South China Sea Region	Balam sundik	Strong	Hard	Good	0.77	Very Durable	Good	Fair
East Indies	Moluccan Ironwood	Strong	Very Hard	Good	0.77	Good	Fair	Fair
Thailand	Deng	Very Strong	Hard	Good	1.10	Good	Good	Plentiful
Thailand	Lumpaw Maca-mong	Very Strong	Hard	Good	0.77	Good	Good	Plentiful
Thailand	Kleng	Strong	Hard	Good	0.90	Good	Good	Fairly Plentiful
Thailand	Rang	Strong	Hard	Good	0.99	Good	Good	Plentiful
Thailand and Burma	Teng	Strong	Hard	Good	1.04	Good	Good	Plentiful
Malaya and Burma	Kojoe Batoe	Strong	Hard	Good	0.98	Durable	Good	Fair
Burma	Pyinkado	Strong	Hard	Good	0.95	Very Durable	Good	Abundant
Borneo	Lizerhout	Very Strong	Very Hard	Good	1.03	Very Durable	Good	Fair
Nepal	Sal	Strong	Very Hard	Good	0.90	Durable	Good	Fair
Nepal	Sandan	Strong	Hard	Good	0.89	Durable	Fair	Fair
Nepal	Dhaura	Strong	Hard	Good	0.92	Durable	Fair	Fair
East Pakistan	Chaplash	Fair	Fair	Good	0.65	Durable	Very Good	Fair
East Pakistan	Nagaswar	Very Strong	Very Hard	Good	1.02	Very Durable	Good	Fair
West Africa	Ekki	Very Strong	Very Hard	Good	0.97	Very Durable	Very Good	Plentiful
West Africa	KoKrodua	Strong	Hard	Good	0.70	Very Durable	Good	Plentiful
Australia	Jarrah	Strong	Hard	Good	0.80	Very Durable	Good	Plentiful
Australia	Ironbark	Very Strong	Very Hard	Good	1.10	Very Durable	Good	Plentiful

MIL-HDBK-1002/5

Figure 1 (Continued)
Properties of Nondomestic Species of Timber

MIL-HDBK-1002/5

3.2.1 Mechanically Laminated Members. Allowable unit stresses for individual pieces used in mechanically laminated members shall comply with those established for sawn lumber. Do not consider adhesives used in combination with nails, spikes, bolts, lag bolts, or wood screws in mechanically laminated members as sharing the stress with the fasteners. Allowable loads in connectors shall conform to the provisions of the NFPA Standard. In vertically laminated beams where spikes are used, provide through bolts or bolts with connectors to prevent separation of the planks. Place two bolts at each end of the beam to hold the ends together. Do not consider transverse joints in the planks as transmitting any stress.

3.2.2 Plywood Members.

3.2.2.1 Built-up Plywood Girders. Observe the following precautions:

a) Allowable shear stress between flanges and web shall not exceed 0.375 times allowable stress in horizontal shear.

b) Web stiffeners shall be screwed or glued to webs and in contact with both flanges. The thickness shall be at least six times the thickness of the web; b/t shall not exceed 8; and minimum web thickness shall be 3/8 inch (9 mm). Stiffeners shall be as wide as the flange. Spacing shall be equal to or less than two times the clear distance between flanges.

c) Provide wood blocks (bearing stiffeners) at points of concentrated load or bearing, or both.

d) For deep girders, reduce the allowable stresses to account for the lack of lateral support of the center fibers as compared to the flange fibers.

3.2.2.2 Stress-Skin Panels. In bending, tension, and compression, consider only those plies where the grain is parallel to the span.

3.2.2.3 Exposure. Where exposed to weather or in humid locations (toilets and shower rooms are examples), use exterior grades of plywood.

3.2.3 Glued, Built-up (Including Laminated) Members. Design standards, procedures, and provisions for individual components (whether plywood or sawn lumber) shall conform to the requirements for such components as previously indicated, except as follows:

3.2.3.1 Transverse Joints. Transverse joints in the planks may be considered as transmitting stress if scarfed joints having a slope not steeper than 1:10 are used. Space joints not less than 24 times the lamination thickness in areas of maximum stress. In lesser stressed areas, spacing may be reduced linearly in proportion to relative stress. Do not use butt joints for structural members.

3.2.3.2 Mechanical Fasteners. Do not use mechanical fasteners in conjunction with glued construction. The movements required to develop the mechanical fasteners are inconsistent with those permitted in glued joints.

MIL-HDBK-1002/5

3.2.3.3 Exposure. Glue-laminated members may be used in exterior exposure and under conditions of exposure to moisture and biologically destructive agents, as they show good resistance to degradation by these agents.

3.2.4 Wood Preservation. The use of treated timbers is recommended under the following conditions and subject to the following requirements.

3.2.4.1 Preservative Treatment. Preservative treatment shall be in accordance with the AWPI Book of Standards. Note the following:

a) Creosote and creosote solutions are not recommended where color, odor, or exudation of the preservative may be undesirable. Waterborne preservatives or oilborne preservatives in volatile solvents should be used.

b) Where cleanliness and paintability are required, preservatives should be of the waterborne type or the oilborne type in volatile solvents.

3.2.4.2 Structural Framing. Pressure preservative treatment for timber should be used under the following conditions of exposure:

a) All wood in contact with ground or water.

b) Wood in contact with masonry or metal, where conduction or condensation creates problems.

c) Roof structures (framing and sheathing) installed over enclosed swimming pools, or in building structures where high humidities prevail.

d) Areas in or near shower rooms, galleys, sculleries, laundry rooms, and cold-storage rooms.

e) Areas of basementless buildings in close proximity to the soil, where moisture and termites can attack the structural elements.

f) All lumber within 18 inches (450 mm) of the ground in slab-on-grade or crawlspace houses (basementless).

g) All structural wood members in regions where dry-wood termites prevail.

h) On waterfront structures, as specified in NAVFAC DM-25 Series.

3.2.4.3 Frame Before Treatment. To the extent practicable, treated wood structures should be framed before treatment. For prefabricated assemblages, consider the feasibility of assembling the structure, then disassembling, treating, and reassembling.

3.2.4.4 Site Requirements. Consult applied biologists during the planning, design, and construction stages for information on wood-destroying pests at the specific site.

MIL-HDBK-1002/5

3.2.5 Fire Retardant Treatment. Follow recommendations in USDA Wood Handbook and in NFPA Fire Protection Handbook. Pressure impregnation is the preferred treatment.

3.2.6 Climatic Influences. Climatic influences for cold and tropic regions are as follows.

3.2.6.1 Cold Region Conditions. Engineering properties usually are not appreciably affected when wood is subjected to extremely low temperatures.

3.2.6.2 Tropical Conditions. Engineering properties of wood are not appreciably affected in tropical climates. However, rot and insect attacks are aggravated in tropical humid areas, and all timber for permanent construction in tropical areas should be preservative treated, except local native hardwoods as discussed in paragraph 3.1.2. See NAVFAC DM-11.01, Tropical Engineering, for details of construction. Structural bonding to other materials should be by means of epoxy resin adhesive. Bonding of wood to wood can be made by a variety of adhesives, such as those covered by Military Specification, MIL-A-22397, Adhesive, Phenol and Resorcinol Resin Base (for Marine Service Use), for marine or severe outdoor use and Federal Specification MMM-A-181, Adhesive, Phenol, Resorcinol, or Malamine Base, for general purposes.

3.2.7 Limited Life Structures. The provisions of DM-2.01 apply. Additionally, disregard the provisions of the design standards relating to decreased allowable stresses for full load, permanently applied, and consider the use of untreated timbers for applications normally requiring treated timber.

3.2.8 Termite Control. See NAVFAC DM-1 Series and NFGS-02250, Soil Treatment for Termite Control. Soil should be treated prior to construction.

MIL-HDBK-1002/5

REFERENCES

AASHTO Standards. Standard Specification for Highway Bridges, American Association of State Highway and Transportation Officials, Washington, DC 20004

AITC publications. Timber Construction Manual, American Institute of Timber Construction, Englewood, CO 80110.

APA publications. American Plywood Association, Tacoma, WA 98401:

Plywood Design Specification
Plywood Folded Plates
Plywood Diaphragm Construction

AREA publications. AREA Manual for Railway Engineering, American Railway Engineering Association, Chicago, IL 60605.

ASTM publications. ASTM-E-380, Standard for Metric Practice, American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

AWPI publications. Book of Standards, American Wood Preservers Institute, Washington, DC 20037.

Military and Federal Specifications and Military Handbooks. Available from U.S. Naval Publications and Forms Center, Philadelphia, PA 19120:

MIL-A-22397	Adhesive, Phenol and Resorcinol Resin Base (for Marine Use)
MMM-A-181	Adhesive, Phenol, Resorcinol or Melamine Base
MIL-HDBK-1008	Fire Protection for Facilities Engineering, Design, and Construction

NAVFAC documents. Available from U.S. Naval Publications and Forms Center, Philadelphia, PA 19120:

NFGS-02250	Soil Treatment and Termite Control
NAVFAC DM-1 Series	Architecture
NAVFAC DM-2.01	Structural Engineering, General Requirements
NAVFAC DM-7 Series	Soil Mechanics, Foundations, and Earth Structures
NAVFAC DM-11.01	Tropical Engineering
NAVFAC DM-25 Series	Waterfront Operational Facilities

NFPA publications. Handbook of Fire Protection, National Fire Protection Association, Batterymarch Park, Quincy, MA 02269.

MIL-HDBK-1002/5

NFPA publications. National Design Specification for Wood Construction, National Forest Products Association, Washington, DC 20036.

Purdue University Agricultural Experiment Station Research Bulletins. Purdue University, Hammond, IN 46323.

No. 814 Determination of Members Stresses in Wood Trusses
with Rigid Joints

No. 727 Design of Glued Joints for Wood Trusses and Frames

TPI publications. Design Specifications for Light Metal Plate Connected Wood Trusses, Truss Plate Institute, Hyattsville, MD 20783.

USDA publications. USDA Wood Handbook, U.S. Department of Agriculture, Washington, DC 20250.

CUSTODIAN:
NAVY - YD

PREPARING ACTIVITY
NAVY - YD

PROJECT NO.
FACR-0178

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER MIL-HDBK-1002/5		2. DOCUMENT TITLE TIMBER STRUCTURES	
3a. NAME OF SUBMITTING ORGANIZATION		4. TYPE OF ORGANIZATION (Mark one)	
b. ADDRESS (Street, City, State, ZIP Code)		<input type="checkbox"/> VENDOR <input type="checkbox"/> EFD/PWD <input type="checkbox"/> USER <input type="checkbox"/> AE <input type="checkbox"/> MANUFACTURER <input type="checkbox"/> CONTRACTOR <input type="checkbox"/> OTHER (Specify): _____	
		5. PROBLEM AREAS	
a. Paragraph Number and Wording:			
b. Recommended Wording:			
c. Reason/Rationale for Recommendation:			
6. REMARKS			
7a. NAME OF SUBMITTER (Last, First, MI) - Optional		b. WORK TELEPHONE NUMBER (Include Area Code) - Optional	
c. MAILING ADDRESS (Street, City, State, ZIP Code) - Optional		8. DATE OF SUBMISSION (YYMMDD)	

REPRODUCED AT GOVERNMENT EXPENSE
 (TO DETACH THIS FORM, CUT ALONG THIS LINE)