

MIL-O-46016(MR)
21 February 1968

MILITARY SPECIFICATION

OIL, QUENCHING

1. SCOPE

1.1 Scope. This specification covers three types of quenching oil.

1.2 Classification. The oils shall be of the following types:

Type I - Slow-speed quench.

Type II - Moderate-speed quench.

Type III - High-speed quench.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

STANDARDS

FEDERAL

Fed. Test Method Std. No. 791 - Lubricants, Liquid Fuels and Related Products; Methods of Testing

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-290 - Packaging, Packing and Marking of Petroleum and Related Products.

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

FSC 9150

MIL-O-46016(MR)

AMERICAN SOCIETY FOR TESTING AND MATERIALS PUBLICATIONS

ASTM Standards on Petroleum Products and Lubricants (Parts 17 and 18)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Material. Each quenching oil shall be a homogeneous petroleum hydrocarbon, with or without additives.

3.2 Physical requirements. The quenching oils shall conform to the requirements for the respective types as specified in table I.

Table I. Physical requirements

Properties	Values		
	Type I	Type II	Type III
Viscosity at 100°F. (37.78°C.)			
Kinematic, cs.	18-25	18-25	18-25
(Saybolt, SUS) ^{1/}	(89-119)	(89-119)	(89-119)
Flash point, °F., minimum	350	350	350
(°C., minimum)	(177)	(177)	(177)
Pour point, °F., maximum	30	30	30
(°C., maximum)	(-1.1)	(-1.1)	(-1.1)
Water, percent by volume, maximum	0.03	0.03	0.03
Contamination, grams, maximum	0.25	0.25	0.25
Quenching speed, percent	15-25	26-35	36-45

^{1/} For information only (see footnote 1, table II).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other

facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Lot.

4.2.1 Bulk lot. An indefinite quantity of a homogenous mixture of material offered for acceptance in a single isolated container; or manufactured in a single plant run (not exceeding 24 hours) through the same processing equipment, with no change in ingredient material.

4.2.2 Packaged lot. An indefinite number of 55-gallon drums or smaller unit containers of identical size and type, offered for acceptance, and filled with a homogenous mixture of material from one isolated container; or filled with a homogenous mixture of material manufactured in a single plant run (not exceeding 24 hours) through the same processing equipment, with no change in ingredient material.

4.3 Sampling.

4.3.1 Sampling for examination of the preparation for delivery. A random sample of containers shall be selected from each lot in accordance with MIL-STD-105 at inspection level II and acceptable quality level (AQL) = 2.5 percent defective, and shall be examined in accordance with 4.4.1.

4.3.2 Sampling for tests. Sampling of a lot for test purposes shall be done in accordance with ASTM method D 270.

4.4 Inspection. Inspection procedures shall be in accordance with method 9601 of Fed. Test Method Std. No. 791.

4.4.1 Examination of the preparation for delivery. Samples selected in accordance with 4.3.1 shall be examined for compliance with MIL-STD-290 with regard to fill, closure, sealing, leakage, packaging, packing, and marking requirements. Any container having one or more defects or under the required fill shall be rejected. If the number of defective or underfilled containers exceeds the acceptance number for the appropriate sampling plan of MIL-STD-105, the lot represented by the sample shall be rejected.

4.5 Classification of tests. All tests are classified as quality conformance tests.

4.6 Test methods. Tests shall be performed in accordance with the applicable methods listed in table II.

MIL-O-46016(MR)

Table II. Test methods

Test	Test method No. Fed. Std. 791	Test method No. ASTM
Viscosity, kinematic		D 445 ^{1/}
Viscosity, conversion of kinematic to Saybolt		D 2161
Flash point		D 92
Pour point		D 97
Water		D 95 ^{2/}
Contamination	3006	
Quenching speed	1110	

^{1/} Kinematic viscosity values shall be determined by ASTM method D 445 and may be converted to Saybolt values by ASTM method 2161, if desired.

^{2/} A 1000-ml round-bottom flask, with an adapter if necessary, shall be used. The sample size shall be 500 ml. The volume of solvent used to dissolve the sample shall be 300 ml.

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing, and marking. Unless otherwise specified in the contract or order, packaging, packing, and marking shall be in accordance with MIL-STD-290.

6. NOTES

6.1 Intended use. The quenching oils covered by this specification are intended for use as quenching media in the heat treatment of metals.

6.2 Ordering data. Procurement documents should specify the following:

- (a) Title, number and date of this specification.
- (b) Type of quenching oil required (see 1.2).
- (c) Level of packaging and packing required (see 5.1).
- (d) Type and size of container required (see 5.1).

MIL-O-46016(MR)

6.3 Storage. The quenching oils covered by this specification may be stored at temperatures ranging from -70° to +120°F. (-57° to +49°C.) without deterioration

Custodian:
Army - MR

Preparing activity:
Army - MR

Review activities:
Army - AV, WC, MU

Project No. 9150-A035

Review/user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

SPECIFICATION ANALYSIS SHEET		Form Approved Budget Bureau No. 119 R004
INSTRUCTIONS		
This sheet is to be filled out by personnel either Government or contractor involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.		
SPECIFICATION MIL-O-46016(MR), Oil, Quenching		
ORGANIZATION		CITY AND STATE
CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT \$
MATERIAL PROCURED UNDER A <input type="checkbox"/> DIRECT GOVERNMENT CONTRACT <input type="checkbox"/> SUBCONTRACT		
1 HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? A GIVE PARAGRAPH NUMBER AND WORDING		
B RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES		
2 COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID		
3 IS THE SPECIFICATION RESTRICTIVE? <input type="checkbox"/> YES <input type="checkbox"/> NO IF YES IN WHAT WAY?		
4 REMARKS (Attach any pertinent data which may be of use in improving this specification. If there are additional papers attach to form and place both in an envelope addressed to preparing activity)		
SUBMITTED BY (Printed or typed name and activity)		DATE

DD FORM 1426
1 APR 63

REPLACES NAVSHIPS FORM 4863 WHICH IS OBSOLETE

FOLD

DEPARTMENT OF THE ARMY
Army Materials and Mechanics Research Center
Watertown, Massachusetts 02172

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding Officer
U.S. Army Materials Research Agency
ATTN: AMXMR-TMS
Watertown, Massachusetts 02172

FOLD